Filing Date: Herewith
Title: BRANCHED POLYMERS CONTAINING IMIDAZOLE GROUPS AND THE PRODUCTION AND USE THEREOF

3. (Amended) Branched polymer according to [one or more of claims 1 and 2] <u>claim 1</u>, wherein the molecular weight of the polymer is 25,000 to 75,000, preferably 30,000 to 50,000.

Page 2

Dkt: 1238.006US1

4. Branched polymer according to [one or more of claims 1 to 3] <u>claim 1</u>, wherein component (A) is optionally a hydroxyalkyl or an alkyl polyalkylene glycol acrylate or methacrylate, a styrene or derivative thereof or a vinyl ether and component (B) is a poly(meth)acrylate with terminal (meth)acrylic function or a monovinyl-terminated polydimethylsiloxane and component (C) is N-vinylimidazole.

A276

**ļ**.i.

-

5. (AMENDED) Branched polymer according to [one or more of claims 1 to 4] <u>claim 1</u>, wherein this is present as a salt of a fatty acid, a hydroxycarboxylic acid, a sulfonic acid, a sulfate, an acidic phosphate or an inorganic acid.

- 6. Process for the production of a branched polymer, characterised in that
  - (A) 50 to 93 wt.% of at least one ethylenically unsaturated monomer,
  - (B) 2 to 25 wt.% of at least one ethylenically unsaturated macromonomer with a molecular weight of 1,000 to 20,000 and
- (C) 5 to 25 wt.% of at least one polymerisable imidazole derivative are polymerised by free-radical polymerisation in the presence of an organic solvant and at least one radical initiator, at a temperature of 50 to 180°C, and the polymer thus obtained is optionally converted to its salt.
- 7. Process according to claim 6, characterised in that the organic solvent is an ester and the radical initiator is a peroxide or an azo compound.

A3 Str

8. (AMENDED) Process according to [one or more of claims 6 and 7] claim 6, characterized in that the reaction temperature is 90 to 150°C.

AY GX

(NEW) A paint, paste or modeling composition comprising a pigment and/or filler and a transhed polymer according to claim 1, wherein the branched polymer is a dispersing agent.